

Crystal Data: Tetragonal. *Point Group:* 4 2m. As dipyratidal crystals to 0.3 mm, displaying {101}, {100}, and rarely {001}.

Physical Properties: *Cleavage:* n.d. *Fracture:* n.d. *Tenacity:* n.d. Hardness = n.d.
D(meas.) = n.d. D(calc.) = 4.26

Optical Properties: Transparent. *Color:* Colorless to pale brown. *Streak:* Colorless.
Luster: Vitreous.
Optical Class: Uniaxial (+). $\omega = 1.727$ $\epsilon > 1.8$

Cell Data: *Space Group:* I4 2d. $a = 6.947(4)$ $c = 6.133(3)$ Z = 1

X-ray Powder Pattern: Stetind quarry, Tysfjord, Nordland, Norway.
3.474 (100), 2.601 (73), 1.786 (68), 4.598 (57), 1.838 (26), 2.772 (25), 1.737 (24)

Chemistry:	(1)
SiO ₂	18.73
Y ₂ O ₃	45.67
Yb ₂ O ₃	11.81
Gd ₂ O ₃	2.09
Tb ₂ O ₃	0.54
Dy ₂ O ₃	2.61
Ho ₂ O ₃	0.62
Er ₂ O ₃	4.72
H ₂ O	[12.2]
Total	98.99

(1) Stetind quarry, Tysfjord, Norway; average of 20 electron microprobe analyses, presence of OH⁻ confirmed by Raman spectroscopy, H₂O calculated for charge balance; corresponding to (Y_{3.11}Yb_{0.46}Er_{0.19}Dy_{0.11}Gd_{0.09}Ho_{0.01}Tb_{0.02})_{Σ=3.99}(Si_{2.4}[H₄]_{0.605})_{Σ=3.01}O₈(OH)₈.

Occurrence: A late, hydrothermal mineral in dissolution cavities in fluorite in niobium-yttrium-fluorine (NYF) type, quartz-microcline pegmatite.

Association: Xenotime-(Y), calcioancylite-(Nd), La-dominant calcioancylite.

Distribution: From the Stetind quarry, Tysfjord, Nordland, Norway.

Name: From Greek “*atels*”, meaning deficient, in allusion to the Si-deficiency of the mineral.

Type Material: Museum of the University of Hamburg, Germany (NO-004).

References: (1) Malcherek, T., B. Mihailova, J. Schlüter, and T. Husdal (2012) Atelisite-(Y), a new rare earth defect silicate of the KDP structure type. European Journal of Mineralogy, 24(6), 1053-1060. (2) (2014) Amer. Mineral., 99, 2151-2152 (abs. ref. 1).