

**Crystal Data:** Monoclinic. *Point Group:* 2/m. As imperfectly formed crystals.

**Physical Properties:** *Cleavage:* Good on {100}. *Tenacity:* Brittle. *Fracture:* Conchoidal. Hardness = 3-3.5 VHN = 199-213 206 average (25 g load). D(meas.) = n.d. D(calc.) = 5.1

**Optical Properties:** Opaque. *Color:* Lead-gray; gray-white in reflected light, deep red internal reflections rare. *Streak:* Dark brown. *Luster:* Metallic. *Anisotropism:* Moderate to weak in brown-violet and deep green tints. *Bireflectance:* Weak. *Pleochroism:* Weak.

*Optical Class:* n.d.

R<sub>1</sub>-R<sub>2</sub>: (400) 39.2-41.6, (420) 38.3-40.9, (440) 37.6-40.4, (460) 37.0-40.0, (470) 36.7-39.7, (480) 36.4-39.5, (500) 35.9-38.9, (520) 35.2-38.3, (540) 34.5-37.6, (546) 34.0-37.2, (560) 33.7-36.8, (580) 32.9-35.8, (589) 32.4-35.4, (600) 32.0-34.9, (620) 31.2-34.0, (640) 30.5-33.1, (650) 30.2-32.8, (660) 29.9-32.4, (680) 29.4-31.9, (700) 29.2-31.6

**Cell Data:** *Space Group:* P2<sub>1</sub>/c. a = 37.612(6) b = 7.8777(12) c = 20.071(3)  
 $\beta = 101.930(2)^\circ$  Z = 1

**X-ray Powder Pattern:** Calculated pattern.  
 3.51 (100), 2.949 (76), 2.751 (73), 2.752 (71), 9.82 (67), 3.86 (63), 2.953 (61)

Chemistry:	(1)	(2)
Tl	7.44	6.97
Pb	37.17	37.70
Sb	1.09	
As	28.99	29.81
S	25.42	25.52
Total	100.12	100.00

(1) Lengenbach quarry, Binntal, Wallis, Switzerland; average of 12 electron microprobe analyses; corresponds to Tl<sub>6.42</sub>Pb<sub>31.68</sub>(As<sub>68.31</sub>Sb<sub>1.59</sub>)<sub>Σ=69.90</sub>S<sub>140.00</sub>. (2) Tl<sub>6</sub>Pb<sub>32</sub>As<sub>70</sub>S<sub>140</sub>.

**Polymorphism & Series:** Anion-omission derivative, N = 3 homeotype of the sartorite homologous series with a nine-fold superstructure. Chemical analysis and/or single-crystal X-ray diffraction is needed to distinguish heptasartorite, enneasartorite and hendekasartorite from one another.

**Occurrence:** In dolostone.

**Association:** Heptasartorite, rathite, baumhauerite.

**Distribution:** At the Lengenbach quarry, Binntal, Wallis, Switzerland.

**Name:** For a member of the *sartorite* homologous series with a nine-fold superstructure.

**Type Material:** Natural History Museum, Vienna, Austria (N 9860).

**References:** (1) Topa, D., E. Makovicky, B. Stoeger, and C. Stanley (2017) Heptasartorite, Tl<sub>7</sub>Pb<sub>22</sub>As<sub>55</sub>S<sub>108</sub>, enneasartorite, Tl<sub>6</sub>Pb<sub>32</sub>As<sub>70</sub>S<sub>140</sub> and hendekasartorite, Tl<sub>2</sub>Pb<sub>48</sub>As<sub>82</sub>S<sub>172</sub>, three members of the anion-omission series of ‘sartorites’ from the Lengenbach quarry at Binntal, Wallis, Switzerland. Eur. J. Mineral., 29(4), 701-712. (2) Makovicky, E., D. Topa, and B. Stoeger (2018) The crystal structures of heptasartorite, Tl<sub>7</sub>Pb<sub>22</sub>As<sub>55</sub>S<sub>108</sub>, and enneasartorite, Tl<sub>6</sub>Pb<sub>32</sub>As<sub>70</sub>S<sub>140</sub>, two members of an anion-omission series of complex sulfosalts from Lengenbach, the Swiss Alps, and comparison with the structures of As-Sb sartorite homologues. Eur. J. Mineral., 30, 149-164. (3) (2018) Amer. Mineral., 103, 828-829 (abs. refs. 1 & 2).