

**Crystal Data:** Monoclinic. *Point Group:*  $2/m$ . Crystals elongated  $\parallel$  [001] or tabular  $\parallel$  {010}; typically striated on {010}  $\parallel$  [001]. Commonly as interpenetrant twins, to 4 cm, alone, in groups, or radiating aggregates. *Twining:* Repeated on {001}, {021}, {110}; three double twins may further twin to simulate a pseudotetragonal prism or dodecahedron.

**Physical Properties:** *Cleavage:* {010} distinct, {001} poor. *Fracture:* Uneven to subconchoidal. *Tenacity:* Brittle. Hardness = 4.5  $D(\text{meas.}) = 2.41\text{--}2.47$   $D(\text{calc.}) = 2.448$

**Optical Properties:** Transparent to translucent. *Color:* Colorless, white, gray, yellow, pink, brown; colorless in thin section. *Streak:* White. *Luster:* Vitreous. *Optical Class:* Biaxial (+). *Orientation:*  $Z = b$ ;  $X \wedge a = 63^\circ\text{--}67^\circ$ . *Dispersion:* Weak, crossed.  $\alpha = 1.503\text{--}1.508$   $\beta = 1.505\text{--}1.509$   $\gamma = 1.508\text{--}1.514$   $2V(\text{meas.}) = \sim 80^\circ$

**Cell Data:** *Space Group:*  $P2_1/m$ .  $a = 9.8688(21)$   $b = 14.1295(7)$   $c = 8.7092(9)$   
 $\beta = 124.74^\circ$   $Z = 2$

**X-ray Powder Pattern:** Korsnäs mine, Finland.  
6.38 (100), 3.13 (80), 2.670 (70), 4.08 (60), 3.24 (60), 3.17 (60), 2.730 (60)

Chemistry:	(1)	(2)	(3)
SiO <sub>2</sub>	48.49	47.52	49.80
Al <sub>2</sub> O <sub>3</sub>	16.35	16.94	14.09
BaO	20.08	20.25	21.18
Na <sub>2</sub> O	trace	1.09	
K <sub>2</sub> O	2.07	1.00	
H <sub>2</sub> O	13.00	13.45	14.93
Total	99.99	100.25	100.00

(1) St. Andreasberg, Germany. (2) Strontian, Scotland. (3) BaSi<sub>6</sub>Al<sub>2</sub>O<sub>16</sub> • 6H<sub>2</sub>O.

**Mineral Group:** Zeolite group.

**Occurrence:** Of hydrothermal origin, in cavities in basalts, phonolites, trachytes; in gneisses, and in some ore veins.

**Association:** Zeolites, calcite, leucite, hyalophane, strontianite, quartz, kaolinite, barite, pyrite, sphalerite, galena.

**Distribution:** Many occurrences; some for well-studied material follow. In Germany, from St. Andreasberg, Harz Mountains; at Idar-Oberstein, Rhineland-Palatinate; and on the Silberberg, near Bodenmais, Bavaria. At Příbram, Czech Republic. From Sarrabus, Sardinia, Italy. Fine crystals from Strontian, Argyllshire, Scotland. From Kongsberg, Norway. At Kupferberg-Rudelstadt, Silesia, Poland. In the Korsnäs lead mine, south of Vaasa, Finland. In Russia, large crystals at Bukan, in the Kotuy River basin, Taimyr. In the USA, from Glen Riddle, Delaware Co., Pennsylvania; at Sing Sing, near Ossining, Westchester Co., New York. In the Beaver mine, Thunder Bay district, Ontario, Canada. At Batopilas, Chihuahua, Mexico.

**Name:** From the Greek *harmos*, for a *joint*, and *tome*, for a *cutting*, as the twinned crystals may be divided.

**Type Material:** Natural History Museum, Paris, France.

**References:** (1) Dana, E.S. (1892) Dana's system of mineralogy, (6th edition), 581–583. (2) Deer, W.A., R.A. Howie, and J. Zussman (1963) Rock-forming minerals, v. 4, framework silicates, 386–400. (3) Sahama, T.G. and M. Lehtinen (1967) Harmotome from Korsnäs, Finland. Mineral. Mag., 36, 444–448. (4) Stuckenschmidt, E., H. Fuess, and Å. Kvik (1990) Investigation of the structure of harmotome by X-ray (293 K, 100 K) and neutron diffraction (15 K). Eur. J. Mineral., 861–874.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.