

Crystal Data: Hexagonal. *Point Group:* 6/m. As aggregates of randomly oriented hexagonal prisms to 250 μm that display {10*0} and {10*1}.

Physical Properties: *Cleavage:* Indistinct on {001}. *Tenacity:* Brittle. *Fracture:* Irregular. Hardness = 3.5-4 D(meas.) = n.d. D(calc.) = 7.32 Nonfluorescent.

Optical Properties: Translucent. *Color:* Colorless. *Streak:* White. *Luster:* Vitreous. *Optical Class:* Uniaxial (-). *n*(calc.) = 2.04

Cell Data: *Space Group:* P6₃/m. *a* = 9.7858(14) *c* = 7.3072(11) *Z* = 2

X-Ray Diffraction Pattern: Copps mine, Gogebic County, Michigan, USA. 2.93 (100), 1.83 (24), 1.94 (23), 3.21 (21), 2.04 (21), 4.08 (18), 1.59 (17)

Chemistry:	(1)	(2)
PbO	82.20	83.41
P ₂ O ₅	15.77	15.91
Cl	0.15	
F	0.46	
H ₂ O	[0.46]	0.67
-O = Cl	0.03	
-O = F	0.19	
Total	98.82	100.00

(1) Copps mine, Gogebic County, Michigan, USA; average electron microprobe analysis supplemented by ATR FTIR spectroscopy, H₂O calculated; corresponding to Pb_{4.97}(PO₄)₃[(OH)_{0.69}F_{0.33}Cl_{0.06}]_{Σ=1.08}. (2) Pb₅(PO₄)₃(OH).

Mineral Group: Apatite supergroup, pyromorphite group.

Occurrence: A geogenic secondary lead phase and not post-mining in origin.

Association: Quartz.

Distribution: From the Copps mine, Gogebic County, Michigan, USA. Other reported localities lack full analytical confirmation.

Name: Prefix, *hydroxyl*, identifies a member of the *pyromorphite* group with dominant (OH)⁻ in the *X* position.

Type Material: Natural History Museum of Los Angeles County, Los Angeles, California, USA (66627).

References: (1) Olds, T.A., A.R. Kampf, J.F. Rakovan, P.C. Burns, O.P. Mills, and C. Laughlin-Yurs (2021) Hydroxylpyromorphite, a mineral important to lead remediation: Modern description and characterization. *Amer. Mineral.*, 106, 922-929. (2) Barinova, A.V., M. Bonin, D.Y. Pushcharovskii, R.K. Rastsvetaeva, K. Schenk, and O.V. Dimitrova (1998) Crystal structure of synthetic hydroxylpyromorphite Pb₅(PO₄)₃(OH). *Crystallography Reports*, 43, 189-192.