

## Hydroxynatropyrochlore

## (Na, Ca, Ce)<sub>2</sub>Nb<sub>2</sub>O<sub>6</sub>(OH)

**Crystal Data:** Cubic. *Point group:*  $4/m\bar{3}2/m$ . As cubic or cube-octahedral crystals, to 0.7 mm, with irregularly shaped cores of amorphous U-Ta-rich hydroxykenopyrochlore.

**Physical Properties:** *Cleavage:* Average on {111}. *Tenacity:* Brittle. *Fracture:* Conchoidal. Hardness = ~ 5 D(meas.) = 4.60(5). D(calc.) = 4.77

**Optical Properties:** Transparent to translucent. *Color:* Pale brown, light brown in transmitted light. *Streak:* White. *Luster:* Adamantine to greasy.

*Optical Class:* Isotropic.  $n = 2.10(5)$

**Cell Data:** *Space Group:*  $Fd\bar{3}m$ .  $a = 10.3275(5)$  Z = 8

**X-ray Powder Pattern:** Kovdor phoscorite-carbonatite pipe, Kola Peninsula, Russia. 2.580 (100), 5.96 (47), 3.110 (30), 1.8257 (25), 2.368 (19), 1.5561 (14), 1.9875 (6)

### Chemistry:

	(1)		(1)
Na <sub>2</sub> O	7.97	Ta <sub>2</sub> O <sub>5</sub>	4.73
CaO	10.38	ThO <sub>2</sub>	5.73
TiO <sub>2</sub>	4.71	UO <sub>2</sub>	3.66
FeO	0.42	H <sub>2</sub> O	[2.37]
Nb <sub>2</sub> O <sub>5</sub>	56.44	F	0.05
Ce <sub>2</sub> O <sub>3</sub>	3.56	$\frac{-O=F_2}{}$	0.02
		Total	100.00

(1) Kovdor phoscorite-carbonatite pipe, Kola Peninsula, Russia; average of 2 electron microprobe analyses supplemented by Raman spectroscopy, H<sub>2</sub>O calculated for weight deficit; corresponds to (Na<sub>1.02</sub>Ca<sub>0.73</sub>Ce<sub>0.09</sub>Th<sub>0.09</sub>U<sub>0.05</sub>Fe<sup>2+</sup><sub>0.02</sub>)<sub>Σ=2.00</sub>(Nb<sub>1.68</sub>Ti<sub>0.23</sub>Ta<sub>0.09</sub>)<sub>Σ=2.00</sub>O<sub>6.03</sub>[(OH)<sub>1.04</sub>F<sub>0.01</sub>]<sub>Σ=1.05</sub>.

**Mineral Group:** Pyrochlore supergroup (general formula - A<sub>2</sub>B<sub>2</sub>X<sub>6</sub>Y); pyrochlore group ( $B = Nb^{5+}$ ).

**Occurrence:** A secondary hydrothermal mineral resulting from the alteration of Nb-rich baddeleyite in low-carbonate phoscorite in the contact zone of a phoscorite-carbonatite pipe with host foidolite as well as in the carbonate-rich phoscorite and carbonatite of the pipe axial zone.

**Association:** Calcite, dolomite, forsterite, hydroxylapatite, magnetite, phlogopite, baddeleyite, barite, barytocalcite, chalcopyrite, chamosite-clinochlore, galena, gladiusite, juonniite, ilmenite, magnesite, pyrite, pyrrhotite, quintinite, spinel, strontianite, valleriite, zirconolite.

**Distribution:** From the Kovdor phoscorite-carbonatite pipe, Kola Peninsula, Russia.

**Name:** For a member of the *pyrochlore* group with prefixes to indicate dominant OH<sup>-</sup> (*hydroxy*) in the Y site and dominant sodium (*natro*) in the A site.

**Type Material:** Mineralogical Museum, St. Petersburg State University, Russia (1/19679).

**References:** (1) Ivanyuk, G.Yu., V.N. Yakovenchuk, T.L. Panikorovskii, N. Konoplyova, Ya.A. Pakhomovsky, A.V. Bazai, V.N. Bocharov, and S.V. Krivovichev. (2018) Hydroxynatropyrochlore, (Na,Ca,Ce)<sub>2</sub>Nb<sub>2</sub>O<sub>6</sub>(OH), a new member of the pyrochlore group from the Kovdor phoscorite-carbonatite pipe, Kola Peninsula, Russia. *Mineral. Mag.*, 83, 107-113. (2) (2018) Amer. Mineral., 103, 2047-2048 (abs. ref. 1). (3) Atencio, D., M.B. Andrade, A.G. Christy, R. Gieré, and P.M. Kartashov (2010) The pyrochlore supergroup of minerals: nomenclature. *Can. Mineral.*, 48, 673-698.