

Crystal Data: Triclinic. *Point Group:* $\bar{1}$. As tabular, on {100}, to prismatic crystals, to 200 μm; in compact nodules and fibrous hemispherical aggregates.

Physical Properties: *Cleavage:* n.d. *Fracture:* n.d. *Tenacity:* n.d. *Hardness =* n.d.
D(meas.) = 2.35 D(calc.) = 2.46

Optical Properties: Transparent to translucent. *Color:* Off-white, snow white. *Streak:* White.
Luster: Earthy, slightly waxy to silky (aggregates).
Optical Class: Biaxial. $n = 1.57$

Cell Data: *Space Group:* $P\bar{1}$. $a = 9.920(4)$ $b = 9.933(3)$ $c = 6.087(2)$ $\alpha = 92.19(3)^\circ$
 $\beta = 100.04(3)^\circ$ $\gamma = 97.61(3)^\circ$ $Z = 2$

X-ray Powder Pattern: Hagendorf-Süd pegmatite, Bavaria, Germany.
9.806 (100), 7.432 (40), 4.119 (20), 2.951 (16), 4.596 (12), 3.225 (12), 3.215 (12)

Chemistry:	(1)
CaO	0.96
MgO	0.12
MnO	14.29
FeO	0.60
ZnO	0.24
Al ₂ O ₃	22.84
P ₂ O ₅	31.62
F	5.13
H ₂ O	2.86
-O=F	2.16
Total	96.50

(1) Hagendorf-Süd pegmatite, Bavaria, Germany; average of 8 electron microprobe analyses, H₂O by CHN, corresponding to (Mn_{0.90}Ca_{0.08}Fe_{0.04}Zn_{0.01}Mg_{0.01})_{Σ=1.04}Al_{2.01}(PO₄)₂[F_{1.21}(OH)_{0.90}]_{Σ=2.11}·5.25H₂O.

Occurrence: A late stage secondary hydrothermal mineral in altered zwieselite-triplite masses in a zoned granite pegmatite.

Association: Apatite-(CaF), sphalerite, uraninite, a columbite-tantalite phase, metastrengite, whiteite-jahnsite (inclusions).

Distribution: From the Hagendorf-Süd pegmatite, Bavaria, Germany.

Name: For *Nordgau*, the oldest name for that part of northeastern Bavaria in which Hagendorf is situated, and where mining has taken place since the 13th century.

Type Material: Museum Victoria, Melbourne, Australia (M48795; M51231).

References: (1) Birch, W.D., I.E. Grey, S.J. Mills, A. Pring, C. Bougerol, A. Ribaldi-Tunncliffe, N.C. Wilson, and E. Keck (2011) Nordgauite, MnAl₂(PO₄)₂(F,OH)₂·5H₂O, a new mineral from the Hagendorf-Süd pegmatite, Bavaria, Germany: description and crystal structure. *Mineral. Mag.*, 75(2), 269–278. (2) (2013) *Amer. Mineral.*, 98, 280–281 (abs. ref. 1).