


Redledgeite



©2001-2005 Mineral Data Publishing, version 1

Crystal Data: Tetragonal, or monoclinic, pseudotetragonal. *Point Group:* $4/m$ or $2/m$.
As dipyrarnidal crystals, to 2 mm; also finely fibrous.

Physical Properties: Hardness = 6.5 D(meas.) = 3.72 D(calc.) = 4.413

Optical Properties: Opaque, transparent on thin edges or in fibrous crystals. *Color:* Black or pale green to dark yellow-green; in reflected light, may have vivid green internal reflections when iron-free. *Luster:* Adamantine.

Optical Class: Uniaxial or biaxial.

R_1 – R_2 : n.d.

Cell Data: *Space Group:* $I4_1/m$, with $a = 14.320(2)$ $c = 5.893(1)$ $Z = 4$, or
Space Group: $I2/m$, with $a = 10.129(2)$ $b = 2.951(1)$ $c = 10.135(1)$ $\beta = 90.05^\circ$ $Z = 1$

X-ray Powder Pattern: Red Ledge mine, California, USA; close to mannardite.
3.195 (100), 2.470 (60), 1.583 (60), 3.570 (50), 1.885 (50), 1.393 (50), 2.217 (40)

Chemistry:	(1)	(2)	(3)
TiO ₂	59.7	58.6	59.72
Fe ₂ O ₃	0.9	1.0	
V ₂ O ₃	0.4	0.7	
Cr ₂ O ₃	17.4	17.0	18.94
BaO	20.2	20.8	19.10
H ₂ O	[2.1]		2.24
Total	[100.7]	98.1	100.00

(1) Red Ledge mine, California, USA; by electron microprobe, Ba + H₂O calculated = 2; corresponds to Ba_{1.06}(Ti_{6.00}Cr_{1.84}Fe_{0.09}V_{0.05})_{Σ=7.98}O₁₆•0.94H₂O. (2) Do.; by electron microprobe, average of 21 analyses; corresponds to Ba_{1.10}(Ti_{5.95}Cr_{1.82}Fe_{0.10}V_{0.08})_{Σ=7.95}O₁₆. (3) BaTi₆Cr₂³⁺O₁₆•H₂O.

Mineral Group: Cryptomelane group.

Occurrence: On chrome ore from a gold deposit.

Association: Chromite, chromian clinocllore, knorringite.

Distribution: In the USA, from the Red Ledge mine, Washington district, Nevada Co., California.

Name: For the Red Ledge mine, California, USA.

Type Material: National Museum of Natural History, Washington, D.C., USA, 95846; The Natural History Museum, London, England, 1928,336.

References: (1) Palache, C., H. Berman, and C. Frondel (1944) Dana's system of mineralogy, (7th edition), v. I, 560 [chromrutile]. (2) Strunz, H. (1961) "Chromrutile" von der Red Ledge Mine ist kein Rutil. Redledgeit. Neues Jahrb. Mineral., Monatsh., 107–111 (in German with English abs.). (3) Strunz, H. (1963) Redledgeit, eine TiO₂–Einlagerungsstruktur analog Kryptomelane. Neues Jahrb. Mineral., Monatsh., 116–119 (in German with English abs.). (4) Scott, J.D. and G.R. Peatfield (1986) Mannardite [Ba•H₂O](Ti₆V₂³⁺)O₁₆, a new mineral species, and new data on redledgeite. Can. Mineral., 24, 55–66. (5) Szymański, J.T. (1986) The crystal structure of mannardite, a new hydrated cryptomelane group (hollandite) mineral with a doubled short axis. Can. Mineral., 24, 67–78. (6) Gatehouse, B.M., G.C. Jones, A. Pring, and R.F. Symes (1986) The chemistry and structure of redledgeite. Mineral. Mag., 50, 709–715.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.