Santarosaite CuB₂O₄

Crystal Data: Tetragonal. *Point Group*: 4 2m. As globules of leaf-like crystals, to 0.06 mm.

Physical Properties: Cleavage: n.d. Fracture: n.d. Tenacity: n.d. Hardness = n.d. D(meas.) = n.d. D(calc.) = 3.96

Optical Properties: Translucent. Color: Vivid blue. Streak: Pale blue.

Luster: Vitreous.

Optical Class: n.d. n = 1.75 (calculated from reflectance data).

Cell Data: Space Group: $I\overline{4}$ 2d. a = 11.517(8) c = 5.632(6) Z = 12

X-ray Powder Pattern: Santa Rosa mine, Northern Chile.

3.797 (100), 3.638 (47), 2.775 (35), 2.572 (26), 2.501 (26), 1.822 (21), 1.793 (20)

Chemistry:		(1
	CuO	43.

CuO	73.27	33.33
PbO	4.48	
CaO	0.97	
B_2O_3	45.44	46.67
Total	94.13	100.00

(1) Santa Rosa mine, Northern Chile; average of 17 electron microprobe and EELS analyses, BO_4 and absence of other anionic groups confirmed by IR and Raman spectroscopy, corresponding to $(Cu_{0.86}Pb_{0.03}Ca_{0.03})B_{2.06}O_4$. (2) CuB_2O_4 .

Occurrence: In the oxidation zone of a hydrothermal polymetallic vein deposit.

Association: Atacamite, malachite, wulfenite, anhydrite.

Distribution: Santa Rosa mine, 15 km SE of Iquique, Atacama desert, Northern Chile.

Name: Named for the mine that produced the first specimens.

Type Material: Mineralogical Museum, University of Hamburg, Germany.

References: (1) Schlüter, J., D. Pohl, and U. Golla-Schindler (2008) Santarosaite, CuB_2O_4 , a new mineral with disordered structure from the Santa Rosa mine, Atacama desert, Chile. Neues Jahrb. Mineral. Abh., 185, 27–32. (2) (2009) Amer. Mineral., 94, 402-403 (abs. ref. 1).