

**Crystal Data:** Orthorhombic. *Point Group:* 2/m 2/m 2/m. As prismatic crystals with {100} and {211} dominant; also spherical and radial fibrous aggregates, to 3 cm.

**Physical Properties:** *Cleavage:* Perfect on {101}, imperfect on {100}. *Fracture:* Conchoidal. *Tenacity:* Brittle. Hardness = ~6 D(meas.) = 3.185 D(calc.) = 3.211

**Optical Properties:** Transparent. *Color:* Colorless to white; colorless in thin section. *Streak:* White. *Luster:* Vitreous, pearly on {100}. *Optical Class:* Biaxial (+). *Orientation:* X = c; Y = a; Z = b. *Dispersion:* r < v. α = 1.609–1.618 β = 1.612–1.619 γ = 1.619–1.628 2V(meas.) = 69.5° 2V(calc.) = 66°40'–70°23'

**Cell Data:** *Space Group:* Pnna. a = 14.465 b = 11.625 c = 5.235 Z = 4

**X-ray Powder Pattern:** Roscommon Cliff, England.  
3.99 (100), 2.89 (100b), 7.25 (80), 1.556 (70), 5.82 (60), 4.54 (60), 3.55 (60)

Chemistry:	(1)	(2)	(3)
SiO <sub>2</sub>	43.1	42.89	42.61
SnO <sub>2</sub>	33.3	35.79	35.62
FeO		0.00	
MnO		0.00	
CaO	13.45	12.86	13.25
H <sub>2</sub> O	8.6	[8.46]	[8.52]
Total	98.45	[100.00]	[100.00]

(1) Roscommon Cliff, England. (2) Do.; by electron microprobe, H<sub>2</sub>O by difference; corresponding to Ca<sub>0.97</sub>Sn<sub>1.00</sub>Si<sub>3.01</sub>O<sub>9</sub>•2.03H<sub>2</sub>O. (3) Corrêgo do Urucum, Brazil; by electron microprobe, H<sub>2</sub>O by difference; corresponding to Ca<sub>1.00</sub>Sn<sub>1.00</sub>Si<sub>3.00</sub>O<sub>9</sub>•2.0H<sub>2</sub>O.

**Occurrence:** On axinite (Roscommon Cliff, England); in miarolitic cavities in a quartz-albite pegmatite (Vězná, Czech Republic).

**Association:** Axinite, cassiterite (Roscommon Cliff, England); albite, titanite, beryl, microlite, quartz (Corrêgo do Urucum, Brazil).

**Distribution:** On Roscommon Cliff, St. Just, and in the Halvosso quarry, Longdowns, Cornwall, England. From Ctidružice and Vězná, Czech Republic. In the Pitkäranta district, Lake Lagoda, Karelia. Large spherical masses of crystals from Corrêgo do Urucum, near Galiléia, Minas Gerais, Brazil. In the USA, in the Himalaya mine, Mesa Grande district, San Diego Co., California. From the Iwaguro Sekizai quarry, Tahara, Gifu Prefecture, Japan.

**Name:** For Sir George Gabriel Stokes (1819–1903), Professor of Mathematics, Cambridge University, Cambridge, England.

**Type Material:** Mineralogical Museum, Cambridge University, Cambridge, England.

**References:** (1) Dana, E.S. and W.E. Ford (1909) Dana's system of mineralogy, (6th edition), app. II, 100. (2) Gay, P. and Rickson, K.O. (1960) X-ray data on stokesite. Mineral. Mag., 32, 433–435. (3) Vorma, A. (1963) Crystal structure of stokesite, CaSnSi<sub>3</sub>O<sub>9</sub>•2H<sub>2</sub>O. Mineral. Mag., 33, 615–616. (4) Couper, A.G. and A.M. Clark (1977) Stokesite crystals from two localities. Mineral. Mag., 41, 411–414.