

Crystal Data: Tetragonal. *Point Group:* $4/m\ 2/m\ 2/m$. As irregular grains, to 150 μm .

Physical Properties: Hardness = n.d. VHN = 812–825 (50 g load). D(meas.) = n.d.
D(calc.) = 6.50

Optical Properties: Opaque. *Color:* Bronze-yellow.

R₁–R₂: (470) 41.2–44.8, (546) 43.9–47.7, (589) 45.6–49.4, (650) 48.2–51.9

Cell Data: *Space Group:* $P4/mmm$. $a = 14.64$ $c = 10.87$ $Z = 8$

X-ray Powder Pattern: Strathcona mine, Sudbury, Canada.

2.80 (100), 2.314 (60), 2.405 (50), 4.35 (40), 3.66 (40), 3.28 (40), 1.868 (40)

Chemistry:	(1)	(2)
Ni	44.1	47.12
Fe	0.9	
Co	0.9	
Bi	22.4	18.63
As	0.0	
Sb	0.0	
Te	8.5	11.38
S	21.9	22.87
Total	98.7	100.00

(1) Strathcona mine, Sudbury, Canada; by electron microprobe; corresponds to (Ni_{8.80}Fe_{0.19}Co_{0.18}) $\Sigma=9.17$ Bi_{1.26}Te_{0.78}S_{8.00}. (2) Ni₉BiTeS₈.

Mineral Group: Hauchecornite group.

Occurrence: In hydrothermal Ni–Co–Cu sulfide veins.

Association: Millerite, chalcopyrite.

Distribution: From the Strathcona mine, Sudbury, Ontario, Canada [TL].

Name: Alludes to its chemical relation to the hauchecornite group.

Type Material: Royal Ontario Museum, Toronto, Canada, M30942.

References: (1) Gait, R.L. and D.C. Harris (1980) Arsenohauchecornite and tellurohauchecornite: new minerals in the hauchecornite group. *Mineral. Mag.*, 43, 877–888.

(2) (1981) *Amer. Mineral.*, 66, 436 (abs. ref. 1). (3) Gait, R.L. and D.C. Harris (1972) Hauchecornite—antimonian, arsenian and tellurian varieties. *Can. Mineral.*, 11, 819–825.