© 2001 Mineral Data Publishing, version 1.2

Crystal Data: Monoclinic, partially metamict. Point Group: 2/m. Massive, to about 1 cm.

**Physical Properties:** Fracture: Conchoidal. Hardness = 5-6 D(meas.) = 3.51-3.65 D(calc.) = 3.64-3.68

**Optical Properties:** Translucent to opaque. Color: Brownish black. Luster: Dull. Optical Class: Isotropic; may be slightly anisotropic. n = 1.639(2)

**Cell Data:** Space Group:  $P2_1/n$ . a = 7.12 b = 7.29 c = 6.71  $\beta = 102^{\circ}41'$  Z = 1

**X-ray Powder Pattern:** Högetveit quarry, Norway. 6.55 (100), 3.42 (80), 3.23 (70b), 2.97 (60), 2.89 (50), 2.40 (40), 7.32 (30)

Chemistry:

|   | (1)   |
|---|-------|
| $SiO_2$   | 15.90 |
| $\bar{\text{ThO}}_2$                              | 0.85  |
| $UO_2$  | 0.57  |
| $Y_2O_3$  | 28.00 |
| $\overline{\mathrm{RE}}_2\overline{\mathrm{O}}_3$ | 19.54 |
| FeO   | 5.52  |
| MnO   | 1.02  |
| MgO   | 0.26  |
| CaO   | 4.88  |
| $P_2O_5$  | 0.00  |
| LOI   | 22.71 |
| Total   | 99.25 |

 $\begin{array}{l} (1)\ \ H\"{o}getveit\ quarry,\ Norway;\ RE\ \ by\ XRF,\ CaO\ \ includes\ 15\%\ SrO,\ loss\ \ on\ \ ignition\ \ taken\ \ as\ \ H_2O;\ RE_2O_3=La_2O_3\ 0.06\%,\ Ce_2O_3\ 0.42\%,\ Pr_2O_3\ 0.08\%,\ Nd_2O_3\ 0.48\%,\ Sm_2O_3\ 0.57\%,\ Eu_2O_3\ 0.05\%,\ Gd_2O_3\ 1.53\%,\ Tb_2O_3\ 0.47\%,\ Dy_2O_3\ 3.85\%,\ Ho_2O_3\ 0.90\%,\ Er_2O_3\ 3.91\%,\ Tm_2O_3\ 0.64\%,\ Yb_2O_3\ 5.79\%,\ Lu_2O_3\ 0.79\%;\ corresponds\ to\ (Y,RE,Ca,Fe,Mn,Mg,Th,U)_4Si_{1.96}H_{8.16}O_{8.11}(OH)_{10.45}. \end{array}$ 

Occurrence: In pegmatite dikes cutting amphibolites.

**Association:** Thalenite, feldspar.

Distribution: In the Högetveit quarry, near Setesdal, Evje, and at Reiarsdal, Norway.

Name: For Professor Thomas Fredrik Weiby Barth (1899-1971), mineralogist and petrologist, Oslo University, Oslo, Norway, who studied the area of first occurrence, and for its *yttrium* content.

Type Material: Oslo University, Oslo, Norway.

References: (1) Neumann, H. and B. Nilssen (1968) Tombarthite, a new mineral from Høgetveit, Evje, south Norway. Lithos, 1, 113–123. (2) (1969) Amer. Mineral., 54, 327–328 (abs. ref. 1).